

Energy Usage and Greenhouse Gas Emissions of Pavement Preservation Processes for Asphalt Concrete Pavements

Lic. Patricia Erica Irrgang
Gerente Latinoamérica Crafcó Inc.

Patricia.irrgang@crafco.com

Jim Chehovits

Crafco Inc.

jim.chehovits@crafco.com

Larry Galehouse

National Center for Pavement Preservation USA

ABSTRACT

Use of pavement preservation treatments extends the remaining service life of asphalt concrete pavements. These treatments typically include spray applied surface seals, thin overlays, crack treatments, chip seals, slurry seal/micro surfacing, surface recycling and others. Each preservation treatment reduces damaging effects of aging and deterioration of the pavement surface layer and helps protect the integrity of the underlying pavement structure. If proactive preservation treatments are not used, pavements deteriorate more rapidly and require major rehabilitation with structural overlays or reconstruction much earlier.

Every type of pavement strategy requires a series of energy using processes that impacts greenhouse gas emissions. Pavement rehabilitation and reconstruction require large amounts of energy to obtain and process raw materials, transport, mix and apply the final product, while pavement preservation processes require much less energy to apply the final product to the road surface. This paper presents information on energy usage per unit area by comparing pavement life extensions of pavement preservation treatments to typical design lives of reconstruction and rehabilitation techniques. Results show that pavement preservation treatments have significantly mitigation energy use and greenhouse gas emissions compared to traditional rehabilitation and reconstruction strategies.

INTRODUCTION

Construction, rehabilitation, and maintenance of highway pavements require obtaining, processing, transporting, manufacturing, and placement of large amounts of construction materials. These activities use substantial amounts of energy and generate green house gasses (GHG). Differing philosophies have existed, and still exist, on the proper approach of managing, rehabilitating, and maintaining pavements.

Methods range from one extreme of allowing the pavement to deteriorate and then reconstructing; to using preservation treatments to minimize effects of aging and

maximize pavement life. Vastly different amounts of energy are consumed with different construction, rehabilitation, and preservation techniques. These various techniques also provide differing amounts of pavement design lives and life extensions.

For each preservation treatment the life extension can be compared to the required energy and GHG emissions to determine an annualized energy use and GHG emission level. To minimize energy and GHG emissions over the life of the pavement, treatments can be chosen as having the lowest annualized energy use and GHG emissions.

LITERATURE REVIEW

Energy use and GHG emissions for the construction industry have been receiving increasing attention in recent years. The terms “Green”, “Sustainable Development”, “Environmental Impact”, “Energy Efficiency”, “Global Warming”, “Green House Gases”, and “Eco-efficiency”, are becoming more widely recognized and used.

For buildings, the Leadership in Energy and Environmental Design (LEED) system has been developed to aid in design and construction to minimize environmental impacts. The LEED-ND (for Neighborhood Development) system includes some basic paving considerations in the analysis for multi-unit developments (US Green Building Council, 2008). The Green roads system has been developed as a method to assess roadway sustainability. Green roads enable owners, consultants and contractors to make informed decisions by providing a sustainability performance metric for roadway design and construction. The system defines roadway sustainability attributes, provides a system for evaluation of roadway sustainability, and includes a collection of sustainable design and construction practices. The system includes 11 project requirements, including items ranging from having pavement preservation and environmental maintenance plans to construction quality control and life cycle cost analysis. Credit can be given for several pavement technologies including warm mix asphalt, cool pavements, and quiet pavements, to name a few. Additional voluntary credits are available that can be added to produce a final Green roads score. The score can be used for tracking and evaluating roadway project and system sustainability (Green roads, 2009). BASF has developed an Eco-efficiency analysis method that can be applied to many products or systems (Uhlman, 2009). The process considers and evaluates six aspects of a system including raw materials, land use, energy consumption, emissions, toxicity potential, and risk potentials. This procedure has been used to compare eco-efficiency of several paving processes including hot mix overlays, micro-surfacing, and chip seals (Wall, 2004). Cold mix systems, such as micro-surfacing were found to use less energy and to be more eco-efficient than hot-mix asphalt concrete, and emulsion chip seals were found to require less energy and be more eco-efficient than hot-applied chip seals. The publication “Road Rehabilitation

Energy Reduction Guide for Canadian Road Builders” (Canadian Construction Association, 2005) was developed to provide information on methods to reduce energy

usage during road construction and maintenance operations. Suggestions are provided for reducing energy use during plant operations and construction operations. Chappat and Bilal (2003) reported an in-depth analysis of energy consumption and GHG emissions of over 20 different paving product types by ton of material placed. Their comparisons show that PCC paving materials and processes demand the most energy, followed by hot mix asphalt (HMA) paving. The report also showed that cold in-place recycling (CIR) is the least energy intensive process. Dorchies (2008) reported on software that has been developed to quantify energy use and GHG emissions for various pavement structures based on material types and quantities. Terrel and Hicks (2008) analyzed energy use for hot in-place recycling (HIR) and determined the process utilizes less energy than hot mix asphalt (HMA) paving. Miller and Bahia (2009) in a report on sustainable pavements revealed that proactive maintenance is the least energy intensive process because minimal improvements are made to the pavement structure and surface course. The authors suggest that cold process patching and surface treatments are the most energy efficient.

Extensive analysis of energy use and GHG emissions for the major construction processes was frequently mentioned in the literature review. For preventive maintenance processes, there is limited reporting of energy use and GHG emissions for several treatments with suitable conclusions. However, available reports do not always use the same base data and analysis methods, so comparisons between processes cannot readily be made.

ENERGY USE AND GHG EMISSIONS FOR CONSTRUCTION MATERIALS

When determining energy use and GHG emissions of various preventive maintenance treatments, the first issue is to determine the components of the process to measure. Some comparisons have been reported which only consider parts of the process, such as manufacturing or product placement. These comparisons can lead to misleading conclusions. A more accurate and realistic measure of energy use and GHG emissions of a specific type of work, is to begin with obtaining the raw materials from the earth and adding all the operation steps, such as transport, refining, manufacturing, mixing and placement. Table 1 was compiled by Chappat and Bilal (2003) of energy consumption and GHG emissions for various construction products. The following discussions of energy use for materials and processes are based on information from Table 1.

Table 1
Energy Use and GHG Emissions for Pavement Construction Materials
(Chappat and Bilal, 2003)

Energy consumed and greenhouse gases emitted during the manufacture of one ton of finished product from extraction (quarry, oil deposit, etc.) until the sale at the production unit (refinery, cement plant, etc.)			
Product	Energy (MJ/t)	CO₂ (kg/t)	Data Source
Bitumen	4,900	285	Eurobitume
Emulsion 60%	3,490	221	Eurobitume
Cement	4,976	980	Athena & IVL
Hydraulic Road Binder	1,244	245	CED
Crushed Aggregates	40	10	Athena & IVL
Pit-Run Aggregates	30	2.5	Athena & IVL
Steel	25,100	3,540	Athena & IVL
Quicklime	9,240	2,500	IVL
Water	10	0.3	IVL
Plastic	7,890	1,100	IVL
Fuel	35	4.0	IVL
Production of Hot Mix Asphalt	275	22	IVL
Production of Warm Mix Asphalt	234	20	IVL
Production of High Modulus Asphalt	289	23	IVL
Production of Cold Mix Plant	14	1.0	IVL
Surface milling of Asphalt for RAP	12	0.8	IVL
In-situ Thermo-Recycling	456	34	Colas MM
In-situ Cold Recycling Stabilization	15	1.13	IVL
In-situ Soil Cement Stabilization	12	0.8	IVL
Laying of Hot Mix Asphalt	9	0.6	IVL
Laying of Cold Mix Materials	6	0.4	IVL
Cement Concrete Road Paving	2.2	0.2	IVL
Lorry Transport (km/t)	0.9	0.06	IVL

Materials

Most materials used in asphalt pavement construction, rehabilitation, and maintenance processes consist of aggregates, of various gradations, and asphalt binders of different performance grades. The total energy used is obtained by starting with the raw material extraction and progressing to transportation and processing/refining.

Aggregates

Energy consumption for aggregate production includes the quarrying, hauling, crushing, and screening. Energy consumption for aggregate production ranges from 30 to 40 MJ/t, and GHG emissions range from 2.5 to 10 kg CO₂/t.

Asphalt

Energy consumption for asphalt binder production includes crude oil extraction, transport, and refining. Energy consumption for asphalt binders has been determined to be 4900 MJ/t, and GHG emissions are 285 kg CO₂/t. For asphalt emulsions, energy consumption is 3490 MJ/t and GHG emissions are 221 kg CO₂/t.

Manufacturing

Manufacturing includes all steps involved with handling, storing, drying, mixing, and preparation of materials for installation. Energy consumed varies depending on the specific material or product type. Typical manufacturing products for highway use include hot mix asphalt (HMA), cold mix, crack sealant, and drying surface dressing aggregate. Production of HMA consumes 275 MJ/t and produces 22 kg CO₂/t. Warm mix asphalt production, as reported in Table 1, consumes 234 MJ/t, approximately 15% less than HMA. It is noted that there are several warm mix asphalt processes for which energy use varies depending on required production temperatures. Cold mix asphalt production only requires 14 MJ/t because of not needing to heat the aggregate to elevated mixing temperatures.

Transport to Work Site

The produced construction materials must be transported to the work site. Energy consumed on transport varies with the distance and the quantity of material moved. Transport energy has been reported as 0.9 MJ/km-t with 0.06 kg CO₂/km-t.

Placement and Construction

Placement and construction consists of all activities required to install the materials or products. This includes traffic control, site and product preparation, compacting, finishing, clean up, waste disposal, etc. The highest energy consuming process for placement is hot in-place recycling (HIR) at 456 MJ/t with 34 kg CO₂/t of GHG. This is due to the required heating to soften and reclaim the existing pavement. Placement of asphalt concrete and cold mixes require 6 to 9 MJ/t with 0.4 to 1.1 kg CO₂/t.

Total Energy Use and GHG Emissions

Tables 2 and 3 are summaries of total energy use and GHG emissions for raw materials, manufacture, transport, and placement of various construction products (Chappat and Bilal, 2003). The data shows that Portland cement concrete pavements use the highest energy consumption at approximately 1000MJ/t with the highest energy demand being required for manufacture of the cement. Asphalt concrete utilizes less energy at 680 MJ/t, with the majority of energy being required for manufacture of the asphalt cement and heating during the hot mix production process.

Table 2(Chappat and Bilal, 2003)
Total Energy Use for Pavement Construction Materials

Energy Consumption (MJ/t) for Each Type of Product						
Product	Binders	Aggregates	Manufacture	Transport	Laying	Total (MJ/t)
Bituminous Concrete	279	38	275	79	9	680
Road Base Asphalt Concrete	196	36	275	75	9	591
High Modulus Asphalt Concrete	284	38	289	79	9	699
Warm Mix Asphalt Concrete	294	38	234	80	9	654
Emulsion Bound Aggregate	227	37	14	81	6	365
Cold Mix Asphalt	314	36	14	86	6	457
Cement-Bound Materials	200	32	14	67	6	319
Cement-Bound Materials & AJ	203	32	14	67	6	323
Aggregate w/Hydraulic Rd.Binder	50	29	14	61	6	160
Aggregate w/Hydraulic Binder & AJ	54	29	14	61	6	164
Cement Concrete Slabsw/oDowe	598	40	14	84	2.2	738
Continuous Reinforced Concrete	1,100	29	14	81	2.2	1,22
Untreated Granular Material	0	40	-	68	6	113
Soil Treated In-situ w/Lime + Cement	63	0	-	7	12	81
Thermo-Recycling	98	4	-	12	456	570
Concrete Bituminous w/10% RAP	250	35	275	73	9	642
Road Base Asphalt Concrete w/20% RAP	157	33	275	64	9	538
Road Base Concrete 30% RAP	137	39	275	58	9	510
Road Base Concrete 50% RAP	98	25	275	47	9	454
Emulsion In-situ Recycling	105	4	-	15	15	139

**Table 3(Chappat and Bilal, 2003)
Total GHG Emissions for Pavement Construction Materials**

Greenhouse Gas Emissions (kg/t) for Each Type of Product						
Product	Binder s	Aggregate s	Manufactu re	Transpor t	Layin g	Total (kg/t)
Bituminous Concrete	16	9.4	22.0	5.3	0.6	54
Road Base Asphalt Concrete	11	7.6	22.0	5.3	0.6	47
High Modulus Asphalt Concrete	17	9.4	23.1	5.0	0.6	55
Warm Mix Asphalt Concrete	17	9.4	20.5	5.3	0.6	53
Emulsion Bound Aggregate	14	9.4	1.0	5.4	0.4	30
Cold Mix Asphalt	20	9.1	1.0	5.7	0.4	36
Cement-Bound Materials	39	5.7	1.0	4.5	0.4	51
Cement-Bound Materials & AJ	40	5.7	1.0	4.5	0.4	51
Aggregate w/Hydraulic Road Binder	10	5.1	1.0	4.1	0.4	20
Aggregate w/Hydraulic Road Binder & AJ	10	5.7	1.0	4.5	0.4	22
Cement Concrete Slabs without Dowels	118	9.6	1.0	5.6	0.2	134
Continuous Reinforced Concrete	188	5.1	1.0	5.4	0.2	200
Untreated Granular Material	0	9.6	-	4.5	0.4	15
Soil Treated In-situ w/Lime + Cement	12	-	-	0.5	1.1	14
Thermo-Recycling	6	1.0	-	0.8	34.2	42
Concrete Bituminous w/10% RAP	15	8.6	22.0	4.9	0.6	51
Road Base Asphalt Concrete w/20% RAP	9	7.8	22.0	4.3	0.6	44
Road Base Asphalt Concrete w/30% RAP	8	7.0	22.0	3.9	0.6	41
Road Base Asphalt Concrete w/50% RAP	6	5.2	22.0	3.1	0.6	37
Emulsion In-situ Recycling	7	1.0	1.1	1.0	0.4	10

ENERGY CONSUMPTION AND GHG EMISSIONS FOR CONSTRUCTION, REHABILITATION, AND PRESERVATION PROCESSES

Different types of pavement construction, rehabilitation, and preservation operations consume different amounts of energy. Energy use and GHG emissions per ton of product provide only a relative comparison of products. The specific pavement structure or work type together with the actual quantities of materials must be evaluated to more accurately compare energy use and GHG emissions for construction, rehabilitation and preservation. Dorchie (2008) performed several comparisons for different structured pavement sections, and determined that for different structures

yielding the same structural performance, energy use and GHG emissions can vary as much as 80%.

For some pavement preservation treatments, including thin HMA overlays and HIR, energy use and GHG emissions are available. There have been some specific comparisons performed for various types of chip seals and for micro-surfacing. No references could be found for fog sealing and crack treatments. To provide uniform comparisons, the information developed by Chappat and Bilal (2003), from Tables 1, 2, and 3 was used to calculate energy use and GHG emissions for typical preservation treatments. Energy use and GHG emissions were calculated per unit area of the pavement surface, using typical quantities of raw materials for each treatment.

Preservation treatments considered include the HMA overlay, HIR, chip seal, micro-surfacing/slurry seal, crack fill, crack seal and fog seal. For some treatments, several different application rates of the treatment were considered. Table 4 shows calculated energy use and GHG emissions for these pavement preservation treatments. The analysis of energy use and GHG emissions considered the entire process for each treatment including raw materials, transport, processing, mixing and installation as appropriate. Further details on energy determinations are listed in the following discussions for each treatment type. For comparative purposes, Table 5 shows energy and GHG emissions for typical pavement construction and rehabilitation work types

Table 4
Total Energy Use and GHG Emission for Pavement Preservation Treatments

TREATMENT	DETAILS	GHG EMISSIONS	
		MJ/m ²	kg/m ²
Hot Mix Asphalt	3.8 cm thickness	59	4.9
	5.0 cm thickness	77	6.7
Hot In-place Recycling (HIR)	3.8 cm thickness; 50/50	49	3.8
	5.0 cm thickness; 50/50	65	4.9
Chip Seal	2.0 L/m ²)Emulsion,	8.9	0.5
	1.6 L/m ² Emulsio	6.5	0.4
Slurry Seal / Micro-surfac.	Type III, 12% Emulsion	6.5	0.3
	Type II, 14% Emulsion	4.9	0.2
Crack Seal	0.37m/m ² ,0.37 kg/m	1.1	0.08
Crack Fill	0.74 m/m ² ,0.74 kg/m	2.0	0.14
Fog Seal	0.23 L/m ² ,50/50 Emuls.	0.4	0.02
	0.46 L/ m ² , 50/50 Emuls	0.8	0.04
	0.69 L/ m ² ,50/50 Emuls	1.2	0.04

Table 5
Energy Use and GHG Emissions for
Asphalt Concrete Pavement Construction and Rehabilitation

TREATMENT	DETAILS	GHG EMISSIONS	
		MJ/m ²	kg/m ²
New Construction	100 mm HMA over 150 mm Aggregate Base ¹	198.5	13.1
Major Rehab Hot Mix Asphalt	100 mm Overlay ²	142.8	11.3
	75 mm Overlay ²	107.1	8.5
Major Rehab Warm Mix Asphalt	100 mm Overlay ²	137.3	11.1
	75 mm Overlay ²	103.0	8.3

¹ Data from Dorchies (2005)

² Data from Chappat and Bilal (2003)

The following are descriptions and findings of the pavement preservation work analyzed:

Hot Mix Asphalt (HMA) Overlay

Thin HMA overlays, placed approximately 3.8 to 5.0 cm thick, are commonly used as a pavement preservation treatment. GHG data are calculated based on using a 2240kg/m³ in-place density. Results are shown in Table 7 for both a 3.8-5.0 cm thickness. The 3.8 cm thickness uses 86 kg/m² and the 5.0 cm thickness uses 114 kg/m².

The analysis used an energy use of 680 MJ/t for the entire process.

Hot In-Place Recycling (HIR)

HIR consists of heating, removing and remixing of one inch of the existing pavement surface followed by installation of a new one inch thick asphalt concrete overlay producing a 5.0 cm thick treatment. For comparison purposes a 3.8 cm total thickness is also shown. Energy use basis is 570 MJ/t. Data are calculated using a kg/m³ in-place density.

Chip Seal

Two chip seal treatment designs were analyzed. First, a high quality design using 0.2 L/m² of asphalt emulsion with 21 kg/m² of aggregate. The second design, a lesser binder application rate of 1.6 L/m² with a smaller aggregate gradation of 15 kg/m². Energy use is calculated including emulsion and aggregate raw materials, transport, and installation.

Slurry Seal/Micro Surfacing

Two slurry seal/micro-surfacing treatment designs were analyzed. First is a typical Type III aggregate, with 12% emulsion and a 13 kg/m² application rate. The second design is a typical Type II aggregate, with a 14% emulsion and an 8.7 kg/m² application rate. Energy use is calculated including emulsion and aggregate raw materials, transport, and installation.

Crack Seal

Crack sealing was calculated for a typical pavement cracking density on the basis of one foot of crack sealing per square yard. This density is equivalent to one full length longitudinal crack per lane, and full width transverse cracks spaced at 11.0 m. This crack pattern, for a typical lane mile produces 2,146 m of cracking for the area of 5,867 m² which is 0.365 m/m². An installation rate of 2268 kg per day is used. The application yields four linear feet per pound of sealant, producing an installation amount of sealant 0.136 kg/m². Energy use is calculated including raw materials, manufacturing, transport, field heating, reservoir cutting, and installation.

Crack Filling

Crack filling was calculated for a typical pavement cracking density of two feet of crack filling per square yard. This density is equivalent to a crack pattern of two full length longitudinal cracks, and full width transverse cracks spaced at 5.5 cm. This crack pattern, for a typical lane mile produces 4,292 m of cracking for the area of 5,867 m², which is 0.73m/m². An installation rate of 2268 kg per day is used. The application yields four linear feet per pound of sealant, producing an installation amount of sealant 0.272 kg/m². Energy is calculated including raw materials, manufacturing, transport, field heating, and installation.

Fog Seal

Fog sealing is calculated for three different application rates 0.23, 0.46, and 0.69 L/m² of a 50/50 water diluted asphalt emulsion. Energy use is calculated including raw materials, manufacturing, transport, and installation.

New Construction: Hot Mix Asphalt (HMA) Pavement

The structural section for the pavement is 100mm of HMA placed on 150mm of compacted aggregate base course. Energy is calculated including raw materials, heating, mixing, transport, placement, and compaction.

Rehabilitation: Hot Mix Asphalt (HMA) Pavement

Both a 100 mm thick HMA overlay and a 75 mm thick overlay were investigated. Energy is calculated including raw materials, heating, mixing, transport placement, and compaction.

Rehabilitation: Warm Mix Asphalt Pavement

Both a 100mm thick warm mix asphalt overlay and a 75mm thick overlay are examined. Energy is calculated including raw materials, heating, mixing, transport placement, and compaction.

ANNUALIZED ENERGY USE AND GHG EMISSIONS FOR CONSTRUCTION, REHABILITATION AND PRESERVATION PROCESSES

Pavement preservation treatments proactively address the pavement needs and are performed to prolong pavement life. There have been several studies that determined the amount of life extension provided by various pavement preservation treatments. The resulting life extensions have varied widely and are dependent on many factors including environmental factors, timing, treatment design, existing pavement distress, traffic levels, and quality of construction. The range of pavement life extensions for properly design and constructed preservation treatments are shown in Table 6. Pavement life extensions provided by preservation treatments range from one year for fog sealing, up to ten years for thin HMA overlays and HIR. The energy and GHG data must be normalized for the expected pavement life extension to appropriately compare energy use and GHG emissions of preservation treatments. The normalization is accomplished by dividing unit area energy and GHG data from Table 4 by the life extensions in Table 6 to produce annualized results. The annualized results for pavement preservation treatments are shown in Table 7 and for new construction and rehabilitation work types in Table 8. In Table 7 the ranges for energy use and GHG emissions are due to the ranges of life extension times listed in Table 6.

Table 6
Pavement Life Extensions Provided by Pavement Preservation Treatments

TREATMENT TYPE	LIFE EXTENSION
Thin HMA Overlay	5 – 10 years
Hot In-Place Recycling	5 – 10 years
Chip Seal	3 – 6 years
Slurry/Micro Surfacing	3 – 5 years
Crack Sealing	1 – 3 years
Crack Filling	1 – 2 years
Fog Sealing	1 year

Table 7
Annualized Total Energy Use and GHG Emission for Pavement Preservation Treatments

Treatment	Details	Pavement Life Extension	GHG Emissions per Year	
			MJ/m ²	kg/m ²
Hot Mix Asphalt	3.8 cm thickness	5 – 10 years	5.9 - 11.8	0.5 - 1.0
	5.0 cm thickness	5 – 10 years	7.7 - 15.4	0.7 - 1.3
Hot In-place Recycling (HIR)	3.8 cm thickness; 50/50 Recycle/New	5 – 10 years	4.9 - 9.8	0.4 - 0.8
	5.0 cm thickness; 50/50 Recycle/New	5 – 10 years	6.5 - 13.0	0.5 - 1.0
Chip Seal	2.0 L/m ² Emulsion, 21 kg/m ² Aggregate	3 – 6 years	1.5 - 3.0	0.08 - 0.10
	1.6 L/m ² Emulsion, 15 kg/m ² Aggregate	2 – 5 years	1.3 - 3.3	0.08 - 0.2
Slurry Seal / Micro-surfacing	Type III, 12% Emulsion, 13 kg/m ²	3 – 5 years	1.3 - 2.2	0.06 - 0.10
	Type II, 14% Emulsion, 8.7 kg/m ²	2 – 4 years	1.2 - 2.4	0.05 - 0.10
Crack Seal	0.37m/m ² , 0.37 kg/m	1 – 3 years	0.4 - 1.1	0.03 - 0.08
Crack Fill	0.74 m/m ² , 0.74 kg/m	1 – 2 years	1.0 - 2.0	0.07 - 0.14
Fog Seal	0.23 L/m ² , 50/50 Diluted Emulsion	1 year	0.4	0.02
	0.46 L/ m ² , 50/50 Diluted Emulsion	1 year	0.8	1.04

	0.69 L/ m ² ,50/50 Diluted Emulsion	1 year	1.2		0.07
--	---------------------------------------------------	--------	-----	--	------

Table 8
Annualized Energy Use and GHG Emissions for
Asphalt Concrete Pavement Construction and Rehabilitation

Treatment	Details	Design Life	GHG Emissions per Year	
			MJ/m ²	kg/m ²
New Construction	100 mm HMA over 150 mm Aggregate Base	20 years	9.9	0.7
Major Rehab Hot Mix Asphalt	100 mm Overlay	15 years	9.4	0.8
	75 mm Overlay	12 years	8.9	0.7
Major Rehab Warm Mix Asphalt	100 mm Overlay	15 years	9.2	0.8
	75 mm Overlay	17 years	8.5	0.7

The annualized energy and GHG data for pavement preservation treatments ranges from 0.4MJ/m²-yr for a 0.23 l/m² fog seal application upwards to 15.4 MJ/m²-yr for 5.0 cm of HMA overlay. Annualized results for the new construction and rehabilitation work types range from 8.5-9.9 MJ/m²-yr. The results group into three categories. The first category includes the thin HMA overlay, HIR, new construction, and rehabilitation, have the highest annualized results ranging from 4.9-15.4 MJ/yd²-yr energy and 0.4-1.3 kg/m²-yr of GHG. The second category includes chip seal, micro-surface, and crack fill at 930 to 1.0-3.3 MJ/yd²-yr energy and 0.07-0.20 kg/m²-yr of GHG. The third and final category includes fog sealing and crack sealing with 0.4-1.1 MJ/m²-yr energy and 0.02-0.08 kg/m²-yr of GHG.

The annualized energy and GHG emission results in Table 7 show that the different pavement preservation treatments provide a year of life extension with differing energy requirements and GHG emissions. Each type of pavement treatment will not always be appropriate for all pavements, distresses, traffic, climate, desired results, etc.

CONCLUSIONS

Comparisons of energy use and GHG emissions for the construction, rehabilitation and preservation of asphalt concrete pavements are calculated and compared. Results show that on an annualized basis, different process types require differing amounts of energy per year of pavement life. New construction, major rehabilitation, thin HMA overlay, and HIR have the highest energy use and range from 3-12.6 MJ/m²-yr. Chip seals, slurry seals, micro-surfacing, and crack filling utilize lower amounts of energy per year of extended pavement life and range from 1.3-3.3 MJ/m²-yr. Crack seals and fog seals use the least amount of energy per year of extended pavement life at less than 1.3MJ/m²-yr.

Energy use and GHG emissions for the different products depend primarily on the type and quantity of materials placed per unit area. Products that use lower amounts of asphalt per unit area and products that do not require heating of aggregate use the least amounts of energy. Additionally, products having the lowest quantity of material applied to the pavement per unit area utilize less energy, simply because not as much material needs to be produced, processed, transported and installed. To minimize energy use and GHG emissions over the life of a pavement, all preservation treatments should be utilized as appropriate to the maximum extent possible for the existing pavement conditions.

REFERENCES

- Dorchies, P.T. (2008). The Environmental Road of the Future: Analysis of Energy Consumption and Greenhouse Gas Emissions. The 2008 Annual Conference of the Transportation Association of Canada, Toronto, Ontario
- Chappat, M. & Bilal, J. (2003). The Environmental Road of the Future: Life Cycle Analysis, Energy Consumption and Greenhouse Gas Emissions, Colas Group.
- Miller, T. & Bahia, H. (2009). Sustainable Asphalt Pavements Technologies, Knowledge Gaps and Opportunities. Modified Asphalt Research Center, University of Wisconsin Madison
- Terrel, R.L. & Hicks, R.G. (2008). Viability of Hot In-Place Recycling as a Pavement Preservation Strategy, Report Number: CP2C-2008-106. California Pavement Preservation Center, Chino, California.
- Uhlman, B. (2009). Principals of Eco-Efficiency Analysis in Construction Applications. ARRA-AEMA-ISSA Annual Meeting, Palm Springs, California. February 17-21, 2009.
- Canadian Construction Association (2005). Road Rehabilitation Energy Reduction Guide for Canadian Road Builders; Ontario
- Wall, C. (2004). Eco-Efficiency Analysis of Chip Seals, BASF Corporation Report.
- US Green Building Council (2008). Leadership in Energy and Environmental Design (LEED). Green Building Rating System, Washington, DC
- Greenroads (2009). University of Washington & CHS M Hull